

PLASGARD 2001®

High Build Vinyl Coating

W
W
W
•
L
O
N
G
P
R
O
D
U
C
T
S
•
C
O
•
U
K

| | |
|-----------------------------|---|
| DESCRIPTION | PLASGARD 2001 is a single pack vinyl co-polymer coating, inertly reinforced. |
| USES | A very flexible coating suitable as an "All Purpose" maintenance or top coating for use in interior or exterior systems, where minimum surface preparing is possible. <i>DRY INSERVICE TEMPERATURE RANGE : up to 85°C</i> |
| <i>Areas of Use :</i> | For use on Pipework, Field repairs, Fabrications and conventional industrial fittings, etc. |
| COLOUR | Red, Black, Grey and Blue. |
| PHYSICAL PROPERTIES | <i>Flash Point</i> 26°C (Abel closed cup) <i>Volume Solids</i> 47% <i>Specific Gravity</i> 1.1 <i>Drying Times at 20°C under well ventilated conditions</i> Surface Dry : 90 minutes Hard Dry : 24 hours Drying times may be extended at lower temperatures. |
| STORAGE | Up to 2 years when stored in original sealed containers at temperatures below 35°C. |
| SURFACE PREPARATION | For application to a wide range of surfaces. Ensure surface is clean and dry and free from oil and grease. Remove all loose matter - rust, scale or other foreign matter. Oil and Grease should be removed with SOLVENT 102. |
| APPLICATION | Ready for use, requires minimum stirring. Normally applied by brush or roller. DO NOT APPLY in rain, snow, etc. or on to wet surfaces. |
| THINNING CLEANING | Thin with up to 25% SOLVENT 102 to assist spray application. Clean all equipment with SOLVENT 102 immediately after use. |
| THEORETICAL COVERAGE | 4.7 sq.m. per litre - subject to surface profile, conditions and application techniques at 100 microns dft. |
| FILM THICKNESS | <i>Wet :</i> 215 microns <i>Dry :</i> 100 microns |
| PACKAGING | PLASGARD 2001 is supplied in 5 litre cans, 1 carton is 4 x 5 litre cans |
| HEALTH & SAFETY | Keep container tightly closed. Wear protective clothing and ensure adequate ventilation. Keep away from sources of ignition. NO SMOKING. Harmful in inhalation, in contact with skin and if swallowed. Material Safety Data Sheets giving full information are available. |

CHASE PROTECTIVE COATINGS LIMITED
Tel. 0044 (0)1797 223561, Fax 0044 (0)1797 224530
Email: info@chaseprotectivecoatings.com